FABRYKA PAPIERU I TEKTURY
BESKIDY

Fabryka Papieru i Tektury Beskidy Sp. z.o.o 34-100 Wadowice, ul.Chopina 1

SELECTION:	CARDBOARD				
composition of the mass:	RECYCLING 100 %				
Quality parameters:	**Method**	**Measure**	**Defined Value**	**Target Value**	**Standard**
base weight	laboratory weight	g/m²	400	±15	PN-EN ISO 536:2012
moisture	waga	%	7	±1	PN-EN ISO 287:2011
strength machine					
tensile strength	MD	N	310	±15	PN-ISO 1924-1
	CD	N	230	±17	PN-ISO 1924-2
water absorptiveness	Cobb'60	%	-	±5	PN-EN 20535, PN-ISO 535
internal bond strength Scott Bond	Scott Bond	J/m²	-	±15	TAPPI T569 pm-00
thickness	thickness gauge	mm	0,87	±0,05	ISO 534, ISO 3034
spot	0,5 - 1mm²	szt	40	max	PN-EN ISO 15755:2002
roll width	standard	mm	1000	±2	-
roll diameter	standard	mm	1200	±2	-
roll weight	standard	kg	500	±30	-
burst	tape and marking on the front part of the roll				-
marking	control label (date, palette, number, weight, shift)				-
Cardboard meets the requirements of the EU Directive 94/62/EC with regard to the content of heavy metals and RP Act of 13 JUNE 2013r on packaging and paskaging waste (Dz.U.z 2013 poz.888)					

Fabryka Papieru i Tektury BESKIDY Sp. z o. o. • ul. Chopina 1 • 34-100 Wadowice • tel. +48 33 873 50 10 • Sąd Rejonowy dla Krakowa-Śródmieścia w Krakowie XII Wydział Gospodarczy Krajowego Rejestru Sądowego KRS 0000858962 • Wysokość kapitału zakładowego 5 130 000,00 zł • NIP 5512012888 • REGON 070864080 • BDO 000035546
Stosownie do art. 4c ust. 1 ustawy z dnia 8 marca 2013 r. o przeciwdziałaniu nadmiernym opóźnieniom w transakcjach handlowych (t.j. Dz.U. z 2023 poz. 1790 ze zm.) Fabryka Papieru i Tektury BESKIDY sp. z o.o. oświadcza, że posiada status dużego przedsiębiorcy w rozumieniu ww. ustawy.
www.paper.com.pl