

Product quality		Classic 2030 Vinyl with HDF core board	Classic 2050 Solid vinyl
Formats		1207 x 216 x 9.6 mm	1209 x 219 x 5 mm
Packaging	Pack:	7 Elements / 1.825 m ² / 17.91 kg	8 Elements / 2.118 m ² / 19.63 kg
	Pallet:	36 Packs / 65.70 m ² / 659.76 kg	42 Packs / 88.96 m ² / 839.46 kg
Tolerances DIN EN 14085 (Vinyl with HDF core board)			Tolerances DIN EN ISO 10582 (Solid vinyl)
Squariness of the elements (≤ 0.50mm)		≤ 0.30 mm	Weight per unit area ≥ 9700 g/m ²
Determination of Linearity (≤ 0.30 mm)		≤ 0.15 mm/m	
Flatness concave / convex	lengthwise (≤ 0.50/≤ 1.0 %)	≤ 0.35/≤ 1.0 %	Squariness of the elements (≤ 0.25 mm)
	wide (≤ 0.10/≤ 0.15 %)	≤ 0.10/≤ 0.10 %	
Surface flushness	(average ≤ 0.15 mm)	average ≤ 0.10 mm	Determination of Linearity (≤ 0.35 mm/m)
	(max. ≤ 0.20 mm)	max. ≤ 0.15 mm	
Opening between installed elements	(average ≤ 0.15 mm)	average ≤ 0.05 mm	≤ 0.20 mm/m
	(max. ≤ 0.20 mm)	max. ≤ 0.10 mm	
Guarantee According Parador guarantee conditions	Domestic area	Lifetime	Notes - Release for glue-down only by PARADOR application technology department - cleaning an maintenance see instructions - technical changes reserved
	Commercial area	10 Years	



Qualität
Fertigung
überwacht
Funktionalität



www.tuv.com
ID 000039917



Classification

	Test method	Rating
Utility class 23 domestic areas with intensive use	EN 14085 DIN EN ISO 10582	Living room, hall, kitchen, home office
Utility class 33 commercial areas with intensive use	EN 14085 DIN EN ISO 10582	Classrooms, small offices, shops
Utility class 42 industrial areas with medium use	EN 14085 DIN EN ISO 10582	Storage rooms or moderately used production areas
Wear layer	EN 429	0.55 mm
Wear behaviour	DIN EN ISO 10582	T
Surface Coating		PUR
Reaction to fire	EN 13501-1	B _{fl} s1
Slip resistance	EN 13893 EN 14041	μ ≥ 0,35 DS
Staining resistance	EN 423	Grade 0, no visible changes
Light fastness	EN ISO 105 – B02	Blue wool scale: Stage ≥ 6
Resistance to roller castor chairs	EN 425	Type W, no visible changes
Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN 12664	Vinyl with HDF core board: 0,068 m ² *K/W Solid vinyl: 0,029 m ² *K/W
Moving a furniture leg	EN 424	No visible changes
Indentation-residual	EN 433	≤ 0,10 mm
Formaldehyde (E1 = 0.1 ppm)		≤ 0,05 ppm
Acoustical - Impact noise reduction	ISO 717-2	Vinyl with HDF core board: 15 dB Solid vinyl: 13 dB (on Akustik-Protect)
Dimensional stability	EN ISO 23999	Vinyl with HDF core board: along and crosswise ≤ 0,1 % Solid vinyl: ≤ 0,25 %
Thickness swelling	ISO 24336 (≤ 18 %)	≤ 16 % (only vinyl with HDF core board)
Antimicrobial activity	ISO 22196	Antibacterial
Slip resistance on an inclined plane	DIN 51130	Brushed / stone texture: R 9 Rough sawn / wood texture : R 10
REACH		Current requirements are complied
Disposal		Private waste disposal with normal household waste / bulky waste possible

Changed:	QMB Parador	File:	20161016_PA_TDS_Vinyl_Classic_EN
Date:	01.06.2012	Updates at:	www.parador.de
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			16.10.2016